

Avigether Classic.

Parameter (unit).	Value.	Standard/ Method.
Size	4,5/5,5 m ² per hide	
Thickness	1,2 +/-0,2 mm	(DIN EN ISO 105- B02)
Light fastness to artificial light	Min. 5 grey scale	(DIN EN ISO 11640)
Dry colorfastness to rubbing	2000 cycles	(DIN EN ISO 11640)
Wet colorfastness to rubbing	500 cycles	(DIN EN ISO 11640)
Flex Resistance	50.000 flex cycles	(DIN 53351)
Finish Adhesion	≥2,5 N 10 mm	(ISO 11644)
Tear Strength	Min. 15 N/mm	(DIN 53329-IUP8)
Stitch tear resistance	Min. 50 N	(DIN 53331-80)
Smoke and Toxicity	On request	Smoke density and Toxicity (ABD0031)



Parameter (unit).	Value.	Standard/ Method.
Emboss	Classic has small emboss. Customized embossing acc.to sample	
Flammability Specification	12 sec. vaertical- Bunsen burner test	CS 25.853 (a), appendix F, ABD 0031- on request
Tannage	Mineral	
Dye	Aniline dyed through	
Range of Colors	60 Colors on stock, customized colors acc. RAL/Pantone can be produced	
Color Match	Tolerance values between 0 and 1, CMC (2:1) by Spectrophometer	
Defects Accepted	Some closed scars, few veins that prove naturalness of the leather	

