

# Carpet Ultralight.

Parameter (unit).	Value.	Standard/ Method.
<b>Total weight</b> [g/m <sup>2</sup> ]	Approx.. 1'540 ± 10 %	EN 1307 / ISO 8543
<b>Pile weight</b> [g/m <sup>2</sup> ]	Approx.. 4.5	ISO 1765
<b>Total thickness</b> [mm]	200	
<b>Pile height</b> [mm]	Approx. 3.0	ISO 1766
<b>Width</b> [cm]	Woven carpet	
<b>Construction</b>	105'500 tufts per m <sup>2</sup>	
<b>Composition (Pile)</b>	100 % Wool, flame retardant	
<b>Ground texture</b>	Synthetic and glass fibres	
<b>Backing</b>	Synthetic latex, flame retardant	
<b>Flame retardant</b>	Approx.. 1'540 ± 10 %	



<b>Classification appearance</b>	Best possible grade and rating	ISO 10361
<b>Color fastness to rubbing</b>	Dry > 4 Wet > 3	ISO 105-X12
<b>Color fastness to light</b>	> 5	EN ISO 105-B02
<b>Color fastness to water</b>	> 3	EN ISO 105-E01
<b>Cleaning</b>	Dry Compound Extraction/ Hot Water Extraction at maximum 40 °C	
<b>Flame retardant</b>		FAR 25.853 (a) Appendix F Part I (a) (1) (ii) EASA CS 25.853 (a) Appendix F Part I (a) (1) (ii) Airbus ABD0031 (AITM 3.0005 + AITM 2.0007 A) Boeing BMS 8-237E (Bss7239 + Bss7238)
<b>Low smoke + toxicity</b>		

